

TUB REGLAZING INSTRUCTIONS

1. **VENTILATE:** IF THERE IS A WINDOW, USE A [WINDOW FAN](#). IF THERE IS NO WINDOW USE AN [EXHAUST SYSTEM](#) AND VENTILATE OUT THE NEAREST WINDOW.
2. **REMOVE CAULK:** USING A 4” SCRAPER, REMOVE CAULK FROM BASE OF TUB. PAY CLOSE ATTENTION TO REMOVE ALL TRACES OF SILICONE AS SILICONE IS A CONTAMINANT.
3. **CLEAN THE SURFACE:** CLEAN THE SURFACE WITH [TOPKOTE’S TUB & TILE CLEANER](#) USING AN [ABRASIVE SCRUB PAD](#) & [80 GRIT WET OR DRY SANDPAPER](#). BE SURE TO RINSE WELL. HEAVILY SOILED TUBS MAY NEED TO BE CLEANED A SECOND TIME.
4. **DRY, MASK AND TACK:** DRY THE SURFACE WITH CLEAN COTTON TOWELS OR PAPER TOWELS, MASK OFF THE AREA AND TACK OFF THE SURFACE TO REMOVE ANY DEBRIS.
5. **APPLY CROSSLINK III:** FOR A STANDARD TUB, APPLY 2 LIGHT COATS (**4-7 OUNCES TOTAL**) OF [CROSSLINK III](#). APPLY ONE COAT HORIZONTAL AND THE SECOND COAT VERTICLE. APPLY THESE TWO COATS BACK TO BACK. WHEN FINISHED APPLYING CROSSLINK III, BLOW THE TUB WITH YOUR TURBINE AIR FOR 2-3 MINUTES THEN APPLY GLAZE.
6. **APPLY GLAZE:** MIX YOUR GLAZE AT A 4-1-2 MIX RATIO (**4 PARTS GLAZE, 1 PART ACTIVATOR AND 2 PARTS REDUCER**). FOR A TYPICAL TUB MIX 12 OUNCES [GLAZE](#), 3 OUNCES [ACTIVATOR](#) AND 6 OUNCES [REDUCER](#). SPRAY 3 COATS ON THE TUB. **APPLY THE FOLLOWING WAY...** FIRST COAT SPRAY A VERY LIGHT “TACK” COAT, BLOW WITH YOUR TURBINE AIR 2-3 MINUTES... SECOND COAT SPRAY A “COVER” COAT (**APPLY JUST ENOUGH GLAZE TO HIDE THE ORIGINAL COLOR OF THE TUB**), BLOW WITH YOUR TURBINE AIR 2-3 MINUTES... THIRD COAT IS THE GLOSS COAT (**HOLD YOUR SPRAY GUN 6-8 INCHES AWAY FROM THE SURFACE AND APPLY A NICE, GLOSSY FINISH**). WHEN DONE SPRAYING, ALLOW THE SURFACE TO DRY FOR 15-20 MINUTES, REMOVE THE MASKING AND CAULK THE BASE OF THE TUB.
7. **GET PAID AND GO HOME!**

FOR APPLICATION ASSISTANCE CONTACT GEORGE PICCOT OR BOB ALEXANDER AT:

GEORGE PICCOT CELL: 803-316-6723 OR BOB ALEXANDER AT 201-906-7993

TO WATCH A VIDEO OF THIS PROCESS, PLEASE VISIT <https://vimeo.com/122638852>.